# Large Format Media Product Information Document



## Glossy Photo Paper - 240 g/m<sup>2</sup> - 6062B

Product Name	Grammage / (g/m²)	Thickness (μ)		Length / m	Mercury Code (EAN128)	Article number	Canon iPF5100	Canon iPF6100	Canon iPF6200	Canon iPF6300	anon iPF63	non iPF60	5	on iPF81	on iPF83	anon iPF80	Canon iPF9100	non iPF90	on iP	Canon iPF610	Canon iPF605	Canon iPF650	Canon iPF655	Canon iPF710	Canon iPF720	Canon iPF750	Canon iPF755	Canon iPF810	Canon iPF815	anon iPF82		LP1	Canon LP24
Glossy	240	245	432	30	6062B001AA	97003192	v	v	v	v	v	v	v	v	v	v	/ v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v
Photo	240	245	610	30	6062B002AA	97003193		v	v	v	v	v	v	v	v	v	/ v	v		v	v	v	v	v	v	v	v	v	v	v	v		v
Paper	240	245	914	30	6062B003AA	97003194								v	v	v	/ v	v						v	v	v	v	v	v	v	v		
	240	245	1067	30	6062B004AA	97003195								v	v	v	/ v	v										v	v	v	v		
	240	245	1524	30	6062B005-AA	97003196											v	v															



**Description:** This top quality photo inkjet paper has a quality photo coating for high grade natural

colour prints of graphic pictures, presentations and photos. The paper is instant dry, is smudge resistant and provides good colour density and excellent image sharpness. This paper is compatible with a large range of dye and pigment digital printing systems, and is the most ideal product for users who need top quality photographic

re-productions.

Features: Extremely quick drying, dye and pigment ink compatible, good colour density,

excellent image sharpness, smudge resistant, lamination not necessary, easy handling.

Applications: Photography, portraits, posters, graphic art reproductions, exhibition graphics,

indoor and outdoor signage.

#### **Physical Properties:**

Weight	240 g/m <sup>2</sup>	±7
Caliper	245 μm	±5
Curl at 23 °C, 50% RH	0 mm	±8
Gloss (Tappi) 75°	73	±5
Opacity	97,0%	
Colour (CIE Lab) D50 /2°	L* 95.5	±0.5
	a* 0.95	±0.5
	h* -7.57	±0.8

**Printing:** For optimum results select the best possible print settings.

Advised Driver / panel settings: Glossy Photo Paper 240gsm / GlossyPhoto 240g

**Finishing:** To add surface protection from dirt, abrasion and gas-fading, lamination is

recommended. Although ink drying is virtually immediate, it is still

recommended to allow a waiting time of approximately 3 hours before lamination. In order to prevent moisture ingress and paper splitting, lamination with a 5-6mm encapsulated edge is also recommended. Laminate must be evenly applied to the

print in order to avoid curling. Both hot and cold lamination is possible.

### **Ideal Storage Conditions:**

Store paper only in original boxes, out of direct sunlight and under normal climatic conditions ( 23 °C, 50% RH ) until ready to use. Allow material to adapt to room conditions before use. Papers can absorb moisture in humid conditions or lose moisture in low humidity conditions. Highly humid conditions make the ink drying time longer and this could interfere with proper laminate adhesion.

#### **Shelf Life:**

2 years from shipping date when stored under ideal conditions (see a above )

'A Whole Wide World of Media Excellence'