

Crystal Point™

Water

(eco) Solvent

UV Curable

Latex

Textiles

IJM579 Polyweave Heavy - B1

235 g/m²

Product Description

B1-certified, 100% polyester, heavy photo textile, with a water-resistant, matt surface, for indoor and short-term outdoor use.

Physical Properties

Thickness	280 µm	ISO 2286-3	Threads per inch	38	
Weight	230 g/m ²	ISO 2286-2	Denier	150 * 600	
Tensile Strength MD/CD	113 / 75 Kg/mm ²		Fire retardant	B1	DIN 4102 B1
Chromaticity L* a* b	93 * 0,84 * -4,60	ISO 13655			

All values listed are target values

Applications/features

Indoor and short-term outdoor signs	Excellent print quality, high image sharpness
Textile banners	Fire retardant B1
Roll-up displays	Moisture resistant
Banner stands	Short-term outdoor (pigment inks)
Wall advertising	Can be cut with hot knife without fraying
Textile blinds (roll-up)	No edge curl under tension

Available Widths (mm)

3" core + 2" adapter	610	914	1067	1524						
----------------------	-----	-----	------	------	--	--	--	--	--	--

Refer for our current offering to www.canon-europe.com/mediaguide

Storage Conditions

Shelf life: 2 years, Temperature 15-25°C, Relative Humidity 20-60%.
Repack opened rolls when not in use. The rolls should be stored hanging from the core plugs inside the box (otherwise striping may occur).

Print Conditions

Best results are obtained at 21°C and 20-60% Relative Humidity.

Environment, Health & Safety

No Material Safety Data Sheet required. Waste not suitable for recycling.

Lamination Compatibility

Cold	Warm	Hot	Cold: pressure sensitive
no	no	no	Warm: heat activated: 85°C - 95°C
			Hot: heat activated: 105°C -130°C

Outdoor Use

This material is developed for pigmented inks and recommended for both indoor and short-term outdoor use. Outdoor durability is up to 6 months, only when pigmented inks are used (results may vary based on application and usage).

Colour Profiles

Canon develops high-quality colour profiles for media / ink / printer / RIP combinations.
Check availability of profiles for your printer on www.canon-europe.com/mediaguide

Canon

Processing Guidelines

Printing guidelines

Side to be printed is the outer side of the roll.
Allow material to adapt to room conditions for 24 hours before printing. It is recommended to handle the media with cotton gloves.
It is recommended to calibrate the printer before printing and to make a test print.
Textiles tend to crease when fed through printers. For minimizing creasing and prevent risk on head-strikes always use the take-up unit of the printer. Increasing the printhead height adjustment will minimize the risk on head-strikes.
To optimize print quality, print-mode should be set for highest print quality.
Ink restrictions and printer settings have to be set for specific printer ink combinations to obtain the best results.
Canon media profiles include recommended ink restrictions and printer parameters. Depending on environment and application, printer parameters may have to be adjusted slightly in order to obtain the best results.

Application guidelines

Allowing the prints to dry at least 24 hours before finishing is strongly advised. When using for banners or other hanging applications, hemming the edges is recommended.
When applying grommets, they should be inserted in double-hemmed edges. Corner grommets should be placed where the length and width hems cross, so that the grommet goes through four layers.
Using glue or pressure sensitive adhesives is not recommended, as this does not prevent the material from natural environmental shrinkage over time.
When you use a “hot-knife” to cut this textile, there will be no fraying.
Laminating guidelines
Liquid laminates are compatible and provide excellent surface protection. Always pretest the liquid laminate for compatibility prior to using. It is not recommended to overlaminate with pressure sensitive laminates because they do not have complete contact with the surface of the textured textile.

Standard disclaimer:

All specifications subject to change without notice. All company and/or product names are trademarks and/or registered trademarks of their respective manufacturers in their markets and/or countries.