

Self-adhesive Specialities

Toner
Water
(eco) Solvent
UVgel / UV
Latex

IJM742 PVC Free Perforated Window Film

100µm

Product Description

PVC Free Perforated, semi gloss PET film (W/B) with a clear, removable adhesive and a double release liner for UV curable inks. For mid to long term exterior-mount applications on glass surfaces for retail and commercial signage, design and architectural applications.

Physical Properties

Vinyl thickness	100 µm	ISO 534	Open area	35%
Weight liner	140 g/m ²	ISO 536	Expected lifetime	5 years
Total Thickness	220 µm	ISO 534	Clean removability	1 year
Perforation size	1.5 mm			

All values listed are target values

Applications/features

Window displays	One way visibility
Shopping centre advertising	Easy application and removal
Bus shelters	Excellent price/quality ratio
	Excellent for UV curable printing
	Clear removable adhesive

Available Widths (mm)

3"core	1372																		
--------	------	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--

Refer for our current offering to www.canon-europe.com/mediaguide

Storage Conditions

Shelf life: 1 year. Temperature 22°C, Relative Humidity 50-55%
 Repack opened rolls when not in use. Allow material to adapt to room conditions for 24 hours before printing.

Print Conditions

Best results are obtained at 20°C and 35-70% RH.

Environment, Health & Safety

No Material Safety Data Sheet required. Waste not suitable for recycling.

Lamination Compatibility

Cold	Warm	Hot	Cold: pressure sensitive Warm: heat activated: 85°C - 95°C Hot: heat activated: 105°C -130°C
Yes*	no	no	

*Use laminate FIN992/FIN993

Outdoor Use

This material is developed for outdoor use. Expected lifetime exterior 5 years (-17°C to 60°C).
 1 year for clean removal. Adhesion may increase with time.

Colour Profiles

Canon develops high-quality colour profiles for media / ink / printer / RIP combinations.
 Check availability of profiles for your printer on www.canon-europe.com/mediaguide



Processing Guidelines

Printing guidelines

Allow material to adapt to room conditions for 24 hours before printing. It is recommended to handle the media with cotton gloves. Make sure that the media comes not into contact with grease, oil, silicon, and dirt to avoid printing defects. Load the media with care in the printers. Incorrect loading can cause skewing or creasing. It is recommended to calibrate the printer before printing and to make a test print. Print results will vary for different printer/ink combinations. Canon media profiles include recommended settings for ink restrictions and printer parameters. Depending on fluctuations in environment, printer, ink, media and applications, printer parameters may have to be adjusted slightly, in order to obtain the best results. Use edge guards to prevent risk on head-strikes at curling edges.

Application guidelines

The application temperature is 15-40°C. Clean the surface with plain soap and water, then rinse and dry the surface well. Remove the release liner and apply the adhesive-backed image to the surface. Once mounted, the image can be cleaned with soap and water. Protect the film from contact with ammonia and solvent-based glass cleaners. For unknown substrates please rest on a small area prior to the final application. Do not overlap seams or edges when mounting a perforated window film. Trim the edges carefully to form a butt seam. Trimming should be done prior to application to avoid scratching the window. It is advised to seal all seams with an edge sealer. This will prevent water and contaminants from getting under the film and obstructing viewing or contaminating the adhesive. Sealer should be applied carefully to completely seal the edges and also to minimize the distortion caused by the sealer from the viewing side of the graphic. Follow all directions of sealer manufacturer to prevent improper application of edge sealer.

Laminating guidelines

Laminate to protect the graphic when exposed to abrasion. Lamination will also prevent water filling up the perforations and impairs visibility when it rains or the window is washed. Laminates will reduce the see-through effect of this film because of reflection. We recommend FIN992 or FIN993 laminate since it has a very high clarity.

Standard disclaimer:

All specifications subject to change without notice. All company and/or product names are trademarks and/or registered trademarks of their respective manufacturers in their markets and/or countries.

Canon Inc.
canon.com

Canon Europe
canon-europe.com

English edition 0116

© Canon Europa N.V., 2022

