


# HP Universal Coated Paper



## The HP Designjet printing system—the complete solution

HP Designjet printers, Original HP inks and printheads, Original HP printing materials and HP Scitex printers, are designed to work together as a system to provide reliable, consistent results with every print.



### **Accomplish more with consistent results**

Look to this economical, recyclable(1, and FSC®-certified printing material, ideal for a variety of graphics and technical applications from presentations and indoor signs to posters that are frequently replaced. From working comps and design proofs to POP signage and special event posters, see high-quality, consistent image quality print to print and roll to roll.

#### Make the economical choice for everyday prints

Meet your everyday printing needs and enjoy consistent, high-quality results with this economical matte coated paper.

#### Add flexibility—this paper is FSC®-certified

Use this high-quality printing material across a broad range of HP Designjet printers. Get added flexibility with this recyclable FSC®-certified paper that supports the development of responsible forest management worldwide.

Target customers	Applications	Benefits	
Architects	Posters and presentations	Consistent, high-quality results	
Engineers	POP and retail displays	Cost-effective for everyday use	
Geographic Information Systems (GIS) professionals	Geographic Information Systems (GIS)	Broad HP Designjet printer compatibility <sup>(2</sup>	
Graphic designers	Architecture (AEC) and engineering (MCAD)	FSC®-certified paper	
Print service providers		Recyclable through commonly available programs	

## **Technical specifications**



#### **HP Universal Coated Paper**

For the latest ICC/media profiles and a variety of resources to help you get the most out of your printer and HP large format printing materials, please visit **globalBMG.com/hp/**.

Weight	90 g/m² per ISO	90 g/m² per ISO 536 Test Method, (24 lbs)					
Thickness	124 microns/4.9	124 microns/4.9 mil per ISO 534 Test Method					
Opacity	89% per TAPPI 1	89% per TAPPI T-425 Test Method					
Brightness	89% per TAPPI 1	89% per TAPPI T-452 Test Method					
Whiteness	117 per CIE Gana	117 per CIE Ganz 82 Test Method					
Finish	Matte	Matte					
Operating temperature	15 to 30° C / 59	15 to 30° C / 59 to 86° F					
Operating humidity	20 to 70% RH	20 to 70% RH					
Dry time	Immediate (at 2	Immediate (at 23° C, 50% RH)					
Shelf life	2 years, unopen	2 years, unopened in original packaging					
Storage temperature	5 to 40° C / 41 to	5 to 40° C / 41 to 104° F					
Storage humidity	10 to 80% RH	10 to 80% RH					
Recyclability	Recyclable thro	Recyclable through commonly available recycling programs					
Country of origin	Product of France	Product of France					
Ordering information	Product numbers	Roll sizes	UPC codes	Region			
	Q1404A <sup>2</sup>	610 mm x 45,7 m (24 in x 150 ft)	848412013689	Worldwide			
	Q1405A <sup>2</sup>	914 mm x 45,7 m (36 in x 150 ft)	848412013696	Worldwide			
	Q1406A <sup>2</sup>	1067 mm x 45,7 m (42 in x 150 ft)	848412013702	Worldwide			
	Q1408A <sup>2</sup>	1524 mm x 45,7 m (60 in x 150 ft)	848412013719	Worldwide			
	SA027A	610 mm x 45,7 m (24 in x 150 ft)	848412014310	Japan			
Warranty		HP large format printing materials are free from defects in materials and workmanship. For warranty statement please see <b>globalBMG.com/hp/MediaWarranties</b> .					

- 1 Recyclable through commonly available programs.
- 2 Requires 2-inch spindle for compatibility with the Latex 260.





Note: Not all FSC\*-certified products

For detailed information on the HP large format print media portfolio and to order, visit  $% \left( \mathbf{r}\right) =\left( \mathbf{r}\right)$ 

globalBMG.com/hp

© 2014 Hewlett-Packard Development Company, L.P. The information contained herein is subject to change without notice. The only warranties for HP products and services are set forth in the express warranty statements accompanying such products and services. Nothing herein should be construed as constituting an additional warranty. HP shall not be liable for technical or editorial errors or omissions contained herein.

