

**Wallpaper Smooth Paste Up ES 180gsm**  
**Graphic Art Range IFA 98**

**Product Description**

Inkjet coated paste up wallpaper designed for value orientated, high volume print shops using eco-solvent printers.

**Features**

- Eco-Solvent, Latex and UV Ink Compatible
- Scratch Resistant Coating
- Suitable For Indoor Application
- No Specialist Knowledge Necessary For Installation
- Compatible With PVA Based Wallpaper Adhesive

**Applications**

- Creative Wall Installations

<b>Basic Weight (gsm)</b>	180		
<b>Paper Thickness (Microns)</b>	225	<b>Paper Thickness (Inches)</b>	0.009
<b>Base Material</b>	Alpha Cellulose		
<b>Coating Type</b>	Eco-Solvent Matte		
<b>Surface Texture</b>	Smooth		
<b>Whiteness (CIE)</b>	92.5		
<b>Brightness (TAPPI)</b>	95		
<b>OBA Content</b>	No		
<b>Opacity (%)</b>	100		
<b>pH</b>	7.5		
<b>Recyclable</b>	Yes		
<b>Notes</b>	For profiles please contact your rip vendor.		

<b>Sheets</b>	
<b>Rolls (25m Length)</b>	60", 54", 30"

Additional Sizes are available on request, subject to order quantity.

**Handling and Storage**

- All digital Fine Art Papers and Canvases are fragile and need to be handled with extreme care. Try not to touch the surface of the paper, always hold the paper by the edges and wear cotton gloves if necessary.
- Return unused material to the original box and only store finished prints in archival quality packaging. If mounting or framing, use only archive grade tapes and glues.
- After printing, leave prints open to the air to fully dry (24 hours is recommended). Do not stack prints on top of each other straight away.
- Using a giclée varnish or spray will help protect your print from damage, effects of UV light and environmental attack.

**Conditions of Use**

- The recommended climate for storage of all papers is 15-20°C, relative humidity of 40-60%. Always store in original packaging, out of direct sunlight and protected from moisture.
- Do not exceed temperatures of 82°C (180°F) when dry mounting.

All recommendations are for your guidance only. These are subject to our test criteria, which remain subject to change without prior notice.