











MEDIATEX® Nero FR (BLOCKOUT)



		Einheit Unit	Norm Standard	Wert Value
Substrat Substrate			DIN 60001	100% Polyester 100% polyester
Bindung Weave			DIN ISO 9354	Gewirke knitted fabric
Flächengewicht Weight		g/m ²	DIN EN ISO 2286-2	210 ± 10
Schrumpf* Shrinkage*		%	190°, 180s	Kette / warp: ≤ 4,5 Schuss / weft: ≤ 2,5
Brandverhalten Fire retardancy			DIN 4102 B1	ja yes
Tintenart Type of ink			<input type="checkbox"/> SUBLI <input type="checkbox"/> UV <input type="checkbox"/> LATEX	Sublimationstinten, UV-härtende Tinten, Latextinten sublimation inks, UV-curable inks, latex inks
Anwendung Application				innen indoor
Breite Width		cm inch	DIN EN ISO 2286-1	max. 310 max. 122
Druckseite Print side				Breite < 3m: Druckseite außen Breite > 3m: Druckseite innen width < 3m: print side outside width > 3m: print side inside
Rollenlänge Roll length		m		30 - 70 ± 0,5

Anwendungen Applications



Blockout / blockout
Banner / banner
Rahmensysteme / framing systems
Spannsysteme / tensioning systems

Besonderheiten Characteristics

- blickdicht
opaque
- dehnbar
stretchable
- kein Weißbruch
no white cracking / crazing
- kalt schneidbar
trimming cold
- kratzfeste Rückseite
scratch-resistant reverse side

* Das Schrumpfverhalten muss vor der Anwendung an dem jeweiligen Drucker geprüft werden; empfohlene Verarbeitungsparameter: 180°C; 30-45s.
The shrinkage has to be tested before printing; recommended processing temperature: 180°C; 30-45s.

All details are nominal values and are subject to change within usual tolerances (± 5%). The information provided in this document is based on current knowledge and experience. They do not exempt a manufacturer/processor from carrying out their own tests and trials as their in-house handling and manufacturing processes can have a significant range of influences on outcomes. Application, utilisation and processing of products is taking place outside of our control and are therefore the sole responsibility of the manufacturer/processor. date: 04/2019