

XPGPP255

Xativa X-Press Gloss Fogra Certified Proofing Paper



A premium Fogra certified, micro-porous resin coated proofing material with a high quality gloss finish and exceptional colour stability.

Ideal for concept plans, client sign off documents and contract proofs.

Produce stunningly accurate proofs with this premium gloss finish proofing paper. Its special micro-porous resin coating provides a exceptional colour stability and a highly reduced metamerism effect even in cases of high applications of ink.

Designed for contract proofs as well as professional colour management its shade fits exactly to the ISO 12647-7 standard and has been awarded Fogra certification as a "gloss proofing paper"

All specifications are correct at time of print and are subject to change without notice. E&OE

Product specifications

Weight	255 g/m ² (+/- 10gsm) ISO536	
Thickness	260 microns (+/- 12 microns) ISO534	
Opacity	> 96% (+/-4%) ISO2471	
Whiteness	92 (+/- 4%) ISO11475	
Finish	Gloss	
Shade	L	95.5 (+/- 2)
	a	0.5 (+/- 2)
	b	-3.3 (+/- 2)
Smoothness	> 500 (Bekk) ISO5627	
Stiffness md	2.4 (+/- 0.8) ISO2493	
Stiffness cd	1.4 (+/- 0.5) ISO2493	
Operating temperature	15 to 100 degrees centigrade	
Operating humidity	20 to 80% RH	
Dry time	Instant dry with heating (at 23 degrees centigrade, 50% RH)	
Shelf time	2 years, unopened in original packaging	
Storage temperature	0 to 40 degrees centigrade	
Storage humidity	5 to 95% RH	
Country of origin	Product of Germany	
Printer / Ink Compatibility	Compatible with all aqueous based dye, pigment and UltraChrome K3 Inks from all leading manufacturers such as Canon, Epson and Hewlett Packard	
Lamination	Can be laminated with commercially available thermal and pressure sensitive films	
Ordering information	Product numbers	Roll Sizes
	XPGPP255-17	432mm x 30m
	XPGPP255-24	610mm x 30m
	XPGPP255-42	1067mm x 30m
Warranty	Xativa large format printing materials are guaranteed to meet Xativa published specifications, to be free of manufacturing flaws and defects, and are designed to resist paper jams when used correctly	

