

XPSP200

Xativa X-Press Satin Fogra Certified Proofing Paper



A semi matt Fogra certified, micro-porous resin coated proofing material with a high quality finish and exceptional colour stability.

Ideal for concept plans, client sign off documents and contract proofs.

Produce stunningly accurate proofs with this premium semi matt finish proofing paper. Its special micro-porous resin coating provides a exceptional colour stability and a highly reduced metamerism effect even in cases of high applications of ink.

Designed for contract proofs as well as professional colour management it has been awarded Fogra certification as a "semi-matt proofing paper"

All specifications are correct at time of print and are subject to change without notice. E&OE

Product specifications

Weight	200 g/m ² (+/- 10gsm) ISO536	
Thickness	207 microns (+/- 12 microns) ISO534	
Opacity	> 94% (+/- 3%) ISO2471	
Whiteness	99 (+/- 4%) ISO11475	
Finish	Semi Matt	
Shade	L	96.5 (+/- 1.5)
	a	0.0 (+/- 0.8)
	b	-1.5 (+/- 0.5)
Smoothness	> 1000 (Bekk) ISO5627	
Stiffness md	30 (+/- 0.5) ISO2493	
Stiffness cd	20 (+/- 0.5) ISO2493	
Operating temperature	15 to 100 degrees centigrade	
Operating humidity	20 to 80% RH	
Dry time	Instant dry with heating (at 23 degrees centigrade, 50% RH)	
Shelf time	2 years, unopened in original packaging	
Storage temperature	0 to 40 degrees centigrade	
Storage humidity	5 to 95% RH	
Country of origin	Product of Germany	
Printer / Ink Compatibility	Compatible with all aqueous based dye, pigment, latex and UltraChrome K3 Inks from all leading manufacturers such as Canon, Epson and Hewlett Packard	
Lamination	Can be laminated with commercially available thermal and pressure sensitive films	
Ordering information	Product numbers	Roll Sizes
	XPSP200-17	432mm x 30m
	XPSP200-24	610mm x 30m
	XPSP200-42	1067mm x 30m
	XPSP200-44	1118mm x 30m
Warranty	Xativa large format printing materials are guaranteed to meet Xativa published specifications, to be free of manufacturing flaws and defects, and are designed to resist paper jams when used correctly	

